

SAFETY & SECURITY FILM

200 Micron – Reflective Silver 20

SA-20RS/200-iSR



Opalux® 200-Micron Reflective Silver 20 combines the benefits of solar heat and glare control with safety and security in the one film installation.

Opalux® combined 200-micron silver 20 is used by Government and commercial organisations where high-performance safety, particularly with reference to risk of bomb-blast, is required along with the features of a solar control film. It is designed to make glass safer, both by strengthening it against breakage and helping hold dangerous shards of shattered glass in situations where breakage does occur. They are suitable for use in applications in the workplace and home. Other benefits can include improved security by creating a deterrent to “smash-and-grab” and forced entry crime, and providing protection against the vandalism of glass through graffiti such as the etching or scratching of glass. Also the combined daytime reflective appearance offers extra privacy protection and excellent heat and glare rejection.

FEATURES

- Excellent solar heat and glare rejection
- Cuts energy use for cooling
- Reflective daytime appearance
- Quick, retro-fit installation
- Scratch-resistant coating
- Screening of harmful UV rays

BENEFITS

- Alleviate the discomfort caused by excessive heat and glare
- Provides the option for solar control still to be provided where an internal installation is deemed not possible or not advisable
- Increased daytime privacy from outside looking in
- Can be used where costly and disruptive large-scale replacement of existing glazing is not a viable option
- Suitable for most non-abrasive window-cleaning methods
- Reduced fading of interior furnishings

PERFORMANCE DATA

SA-20RS/200-iSR

SOLAR ENERGY	Transmitted	11%
	Reflected	48%
	Absorbed	41%
VISIBLE LIGHT	Transmitted	17%
	Reflected (Interior)	54%
	Reflected (Exterior)	51%
UV Rejection		99%
Glare Reduction		81%
Shading Coefficient		0.26
Solar Heat Gain Coefficient (G-Value)		0.23
U-Value (W/m²K)		6.13
Total Solar Energy Rejected		77%
Product Warranty		10 years

PHYSICAL PROPERTIES

Description	Dark Tint
Film Thickness	200-Microns (8-thou)
Structure	Multi Ply Laminate
Tensile Strength	28,500 PSI
Break Strength	220 Pounds per Inch (width)
Adhesive Type	Acrylic Pressure Sensitive
Peel Strength	6 to 7 Pounds per Inch

NOTES

Test results are produced from film applied to 3mm clear single glass. Performance data is subject to change without prior notice. Accurate selection of window film requires specialist knowledge, and it is recommended that specifiers contact the company at the specification stage. It is the users' responsibility to ensure the product is suitable for the intended use. The seller shall not be liable for any direct, indirect or consequential loss or damage howsoever arising.

SPECIFICATION

The safety and solar control film is to be Opalux® SA-20RS/200-iSR, as manufactured by Opalux® (www.opaluxwindowfilms.com). The window film is to be installed to the interior side of the glass, and the unique product roll numbers used are to be registered in accordance with the manufacturer's warranty procedure.